

F.I.E. BALCONI S.R.L.
Vimercate MB) - Italy

email: info@balconisrl.it
Website: www.balconisrl.it

TEL 0039039667541

DATA SHEET OF D. 19.61

DATE
09/2003

PAG. 1/1

CODE	OUR TYPE	DETAILS
19	D 19.61	EXTRUDED SILICONE ELASTOMER TUBE
		<ul style="list-style-type: none">• CLASS C• OPERATING TEMPERATURE: from - 50°C to + 200°C continuous• DIELECTRIC STRENGTH FROM KV 4 TO KV 20

It's the most flexible and elastic tube with outstanding dielectric properties.

DETAILS

- Specific gravity	DIN 53479	g/cm ³	1,200 +/- 0,020
- Hardness	DIN53505	shore	70 +/- 5
- Tensile strength	DIN 53504	MPa	8 min.
- Elongation at break	DIN 53504	%	250 min.
- Tear resistance	ASTM D624B	KN/m	15 min.
- Compression set Sch. 25% 175°C 22h	DIN 53517	%	da 21 a 37

**REGULATIONS:
REACH - ROHS 2 RULES**

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the product for a particular purpose